

(19) 世界知的所有権機関
国際事務局(43) 国際公開日
2004年5月27日 (27.05.2004)

PCT

(10) 国際公開番号
WO 2004/043642 A1(51) 国際特許分類⁷: B23K 20/12

(21) 国際出願番号: PCT/JP2003/014414

(22) 国際出願日: 2003年11月13日 (13.11.2003)

(25) 国際出願の言語: 日本語

(26) 国際公開の言語: 日本語

(30) 優先権データ:
特願 2002-329847
2002年11月13日 (13.11.2002) JP

(71) 出願人 (米国を除く全ての指定国について): 日本軽金属株式会社 (NIPPON LIGHT METAL CO., LTD.) [JP/JP]; 〒140-8628 東京都品川区東品川二丁目2番20号 Tokyo (JP). 東洋アルミニウム株式会社 (TOYO ALUMINIUM KABUSHIKI KAISHA) [JP/JP]; 〒541-0056 大阪府大阪市中央区久太郎町三丁目6番8号 Osaka (JP).

(72) 発明者; および

(75) 発明者/出願人 (米国についてのみ): 岡庭 茂 (OKANIWA, Shigeru) [JP/JP]; 〒421-3203 静岡県庵原郡蒲原町蒲原1丁目34番1号 日本軽金属株式会社 グループ技術センター内 Shizuoka (JP). 楠井潤 (KUSUI, Jun) [JP/JP]; 〒541-0056 大阪府大阪市中央区久太郎町三丁目6番8号 東洋アルミニウム株式会社内 Osaka (JP). 西山 俊正 (NISHIYAMA, Toshimasa) [JP/JP]; 〒950-3101 新潟県新潟市 太郎代

1572-19 日本軽金属株式会社 新潟工場内 Niigata (JP). 石井 秀樹 (ISHII, Hideki) [JP/JP]; 〒421-3203 静岡県庵原郡蒲原町蒲原1丁目34番1号 日本軽金属株式会社 グループ技術センター内 Shizuoka (JP). 堀 久司 (HORI, Hisashi) [JP/JP]; 〒421-3203 静岡県庵原郡蒲原町蒲原1丁目34番1号 日本軽金属株式会社 グループ技術センター内 Shizuoka (JP).

(74) 代理人: 小倉 亘 (OGURA, Wataru); 〒171-0043 東京都豊島区 要町三丁目23番7号 大野千川ビル201 Tokyo (JP).

(81) 指定国 (国内): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) 指定国 (広域): ヨーロッパ特許 (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

添付公開書類:
— 国際調査報告書

2文字コード及び他の略語については、定期発行される各PCTガゼットの巻頭に掲載されている「コードと略語のガイダンスノート」を参照。

(54) Title: METHOD FOR JOINING ALUMINUM POWDER ALLOY

(54) 発明の名称: アルミニウム粉末合金の接合方法



(57) Abstract: A method for joining aluminum powder alloy articles which comprises pressurizing and sintering an aluminum alloy powder prepared through the rapid solidification method to form a sintered article, and then joining the resultant articles by using the friction agitation joining method; the method which comprises using a composite sintered article containing ceramic particles dispersed therein; and the method comprising carrying out the friction agitation joining with a joining auxiliary containing ceramic particles of similar material to that of articles to be joined which is sandwiched between or placed on the articles. The method allows the articles to be joined without melting, that is, without the occurrence of blowholes or the roughening of their structure, which results in the achievement of joining with the retention of characteristics inherent in the original aluminum powder alloy.

(57) 要約: 急冷凝固法で得たアルミニウム合金粉末の加圧焼結体を摩擦撹拌接合法により接合する。加圧焼結体としては、セラミックス粒子を分散させた複合焼結体でもよい。被接合部材間あるいは被接

合部上に接合する部材と同種のセラミックス粒子を含有する接合補助材を扶持または載置した状態で摩擦撹拌接合してもよい。接合部は溶融されることなく接合されるので、ブローホールの発生や組織が粗大化することがなく、アルミニウム粉末合金の本来の特性を維持したまま接合される。

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/14414

A. CLASSIFICATION OF SUBJECT MATTER

Int.Cl⁷ B23K20/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int.Cl⁷ B23K20/12

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Jitsuyo Shinan Koho	1922-1996	Jitsuyo Shinan Toroku Koho	1996-2004
Kokai Jitsuyo Shinan Koho	1971-2004	Toroku Jitsuyo Shinan Koho	1994-2004

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 2001-47261 A (Sumitomo Light Metal Industries, Ltd.), 20 February, 2001 (20.02.01), Claims; detailed explanation of the invention; Par. Nos. [0019] to [0031]; Figs. 1 to 5 (Family: none)	1-8
P, A	JP 2002-346770 A (Hitachi, Ltd.), 04 December, 2002 (04.12.02), Full text; all drawings (Family: none)	1-8

☒ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

* Special categories of cited documents:
 "A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier document but published on or after the international filing date
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
 "&" document member of the same patent family

Date of the actual completion of the international search
29 January, 2004 (29.01.04)

Date of mailing of the international search report
10 February, 2004 (10.02.04)

Name and mailing address of the ISA/
Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/14414

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, A	JP 2003-149382 A (Mitsubishi Heavy Industries, Ltd.), 21 May, 2003 (21.05.03), Detailed explanation of the invention; Par. Nos. [0007], [0013], [0049], [0065]; Figs. 1 to 5 (Family: none)	1-8